ABSTRACT

The present invention provides hot dip galvanized high strength steel sheet excellent in plating adhesion 5 and hole expandability and a method of production of the same, that is, hot dip galvanization steel sheet excellent in plating adhesion and hole expandability containing, by mass%, C: 0.08 to 0.35%, Si: 1.0% or less, Mn: 0.8 to 3.5%, P: 0.03% or less, S: 0.03% or less, Al: 10 0.25 to 1.8%, Mo: 0.05 to 0.35%, and N: 0.010% or less and having a balance of Fe and unavoidable impurities, said hot dip galvanized high strength steel characterized in that the steel sheet has a metal structure having ferrite, bainite, by area percent, 0.5% to 10% of 15 tempered martensite, and, by volume percent, 5% or more of residual austenite, and a method of production comprising annealing by a continuous annealing process at 680 to 930°C in temperature, then cooling to the martensite transformation point or less, then hot dip 20 galvanizing the steel during which heating the steel to 250 to 600°C, then hot dip galvanizing it.